

**PRODUCT**

Pharmaceutical push through foil, unprinted

**MATERIAL COMPOSITION**

Primer for printing / Aluminium 20µm hard tempered / 20 g/Sqm lacquered PVDC

Stratigraphy composition	Code	Thickness (µm)		Weight (g/m <sup>2</sup> )		Chemical composition
		Value	Tol.	Value	Tol.	
Primer	CT311	-	-	0,8	± 0,2	Polyester
Aluminium hard tempered		20,0	± 1,6	54,0	± 4,3	DIN EN 573-3 EN AW 8079
Heat seal	CT299	-	-	20,0	± 2,0	PVDC dispersion
<b>Overall</b>		<b>35,2 (*)</b>	<b>± 3,2 (*)</b>	<b>74,8</b>	<b>± 6,5</b>	

(\*) Obtained from grammage

**MATERIAL PROPERTIES**

Residual solvent (IO 13)	<= 10 mg/m <sup>2</sup>
Varnishes adhesion to the substrate (IO 06)	No detachment
Bonding to PVDC (IO 05)	>= 9 N/15mm (220°C - 267 N/cm <sup>2</sup> - 1 second - 180°)
FT-IR Spectra heat-seal lacquer compare (IO 34)	>= 98,5 %
Melting point of thermosealable varnish (IO 17)	100 °C ± 10
Primer for printing resistance to temperature (IO 11)	<= 290 °C
Water vapor permeability (DIN ISO 15106-3)	<= 0,01 g/m <sup>2</sup> (24h - 38°C / 90% r.h. and 25°C / 100% r.h.)
Oxygen permeability (DIN 53 380-3)	<= 0,005 cc/m <sup>2</sup> (24h - 23°C / 50% r.h. and 25°C / 50% r.h.)

**CLEARANCE CERTIFICATE**

<b>Product</b>	This laminate is registered at the Food and Drug Administration with the DMF number 11322. CE Regulation 1935/2004 - 1895/2005 - 2023/2006 (GMP). Directive 94/62/CE and CONEG. EMEA/410/01. It doesn't contain phthalates.
<b>Nitrosamines statement</b>	The product is Nitrosamines-free. The product doesn't include within its composition nor Nitrosamines as such neither possible precursors of the same. The absence of such chemicals is excluded both by our raw material suppliers and specific analysis, performed periodically, in order to exclude the presence of such chemicals also as Not Intentionally Added Substances as well as impurities/contaminants. Anyhow Aluberg doesn't check each batch produced for Nitrosamines presence, and a.m. analysis are conducted on scheduled base.
<b>Thermosealable lacquer</b>	FDA 21 CFR § 175.300 - 175.320 - 178.3400 (Registered at FDA with DMF 8738) Directives 2002/72/CE - 2004/19/CE - 2005/79/CE - 2007/19/CE CE Regulation n. 10/2011 Resolution of the Council of Europe AP(2004)1 European Pharmacopoeia paragraphs 3.1.11 and 3.2.2

**WARRANTY, STORAGE AND SHELF-LIFE**

This warranty is only valid if the following conditions of storage are observed:

<b>Condition of storage</b>	Recommended storage conditions: - no direct sunlight - room temperature between 18°C - 30°C (optimum 18°C - 20°C) - relative humidity between 40% and 60% (optimum 40% - 50%)
<b>Workability</b>	Maximum 2 years from delivery date for sealing. Maximum 6 months from delivery date for printability.
<b>Function</b>	Maximum 5 years after processing on the packaging line.

**LIABILITY EXCLUSION**

Data mentioned in the technical specification, obtained in our laboratory or in our raw material supplier's laboratories, are valid as a general indication for the use of the product.

So, even if valid, they don't bind our Company that can not check the conditions of their use.